

PLANOFINISH PU 2KS

Solvent based aliphatic polyurethane varnish glossy finish

- ▷ **High resistance to UV radiation**
 - ▷ **Suitable for PLANOCOLOR Microcement coatings in swimming pools**
 - ▷ **Suitable for external floor applications**
 - ▷ **High resistance to friction and mechanical stresses**
 - ▷ **Suitable for protecting epoxy paints and coatings**
-

Description

PLANOFINISH PU 2KS is a two-component aliphatic polyurethane varnish with multiple UV filters and high resistance to sunlight and weather conditions, suitable for indoor and outdoor applications. Suitable for application to PLANOCOLOR PREMIUM SP cement screeds in swimming pools and outdoor (PREMIUM SP & 2K) giving a glossy look. Due to its excellent mechanical strength, it significantly improves surface protection from damage when applied to epoxy paints or floor coatings. It has high adhesion even on metal and natural stones.

Certifications

Complies with Directive 2004/42/EC for two-component special coatings (product subcategory i, type D) with a maximum VOC content of less than 500 g/L. The VOC of the final product to be used is less than 500g/L.

Typical Applications

PLANOFINISH PU 2KS can be used to protect and enhance surfaces such as:

- Micro-cement screeds PLANOCOLOR PREMIUM 2K for outdoor use and floors with heavy use in homes, hotels, parking areas, outdoor benches and built furniture
- Micro-cement screeds PLANOCOLOR PREMIUM SP in swimming pools, hot tubs, steam baths, built-in showers and in general areas that are permanently immersed in water
- Self-leveling epoxy coverings or floor paints such as epoxy systems PLANOCOLOR EPOXY or PLANOCOLOR LIQUID GLASS in order to increase surface strength in mechanical loads.
- Karystos type stones and in general stones in external areas
- Industrial floors made of concrete and scattered with hardener such as NOVADUR S in industries, parking areas, gas stations, ramps
- Non-absorbent surfaces such as galvanized metal sheets, polyester

Technical Data

Product Identification

	Component A	Component B
Consistency	Liquid	Liquid
Color	Transparent	Transparent
Chemical base	Aliphatic polyurethane	Catalyst
Specific gravity	0,98 – 1,2 kg/l	1,01 kg/l
Storage	12 months in a dry place in the original sealed packaging	

Application Data (+23°C % & 50% R.H.)

Mixing ratio	Part A : Part B \approx 3,6 : 1,4
Specific gravity of the mix	1,05 \pm 0,05 kg/L
Working time	1 hour -> 30°C & 2 hours -> 25°C & 2,5 hours -> 12°C
Temperature application	from +12°C up to +30°C
Walkability	24 hours -> 25°C & 36 hours -> 12°C
Reapplication time	24 hours for temperature <23°C & 12 hours for temperature > 30°C
Full polymerization time	7 days at 25°C

Final Performances

	Performance
Gloss (gloss 60°)	60
Abrasion resistance	42mg Tabertest ASTM D 4060 (CS 10/1000/1000)
Adhesion resistance	\geq 2,4 N/mm ²
Resistance to temperature change (dry charge)	from -30°C up to +80°C
Flexibility (torsion test)	Successful (ASTM D522, 180° bend, 1/8"m)

Application Procedure

Substrate preparation

The surface to which PLANOFINISH PU 2KS is to be applied should be clean, dry, and free from dust. The substrate must be insulated and not subject to rising moisture. The maximum permissible moisture content of the substrate must not exceed 4%. The application surface temperature should be between + 12°C and + 30°C, otherwise, the varnish will not dry properly, might “break” and discoloration may occur.

Preparation of the mix

Components A and B are in containers with a predetermined mixing ratio. Component B is completely added to component A. Mixing of the two components is done for about 2 - 3 minutes with an electric mixer at low speed.

Application of the mix

Apply the mix in 2 at least continuous layers by means of a suitable varnish roller. The number of layers is determined by the type of application. In any case, ensure that the varnish penetrates well into the surface. The waiting time between layers is 24 hours when the temperature is less than + 23°C and 12 hours when the temperature is higher than +30°C.

When applied to swimming pools upon PLANOCOLOR PREMIUM SP micro-cement we apply 3 layers of PLANOFINISH PU 2KS. At the swimming pool emphasis should be given to the corners at the base of the pool where the material should be applied by paintbrush to seal them properly.

In micro-cement coatings such as PLANOCOLOR PREMIUM 2K when the application is outdoors, apply a first layer of DRY BRIGHT diluted 1:1 in water and then 2 PLANOFINISH PU 2KS layers. In this way we avoid color alterations in the final surface since this risk is significantly reduced using DRY BRIGHT. In any case, however, if there are any doubts, it is recommended to perform a trial application. PLANOFINISH PU 2KS can also be applied to increase the surface strength of epoxy coatings such as PLANOCOAT EPX, PLANOFLOOR EPX or PLANOCOLOR LIQUID GLASS. In these cases, the product is applied in one layer without interruption. The aesthetic effect is a glossy surface with increased resistance to wear.

Maintenance

Daily cleaning of surfaces treated with PLANOFINISH PU 2KS is done with neutral cleaners such as NEUTRAL CLEANER undiluted or diluted in water depending on the application. For special cleaning cases such as black rubber stains, household stains, wax etc. it is recommended to use ALCALINE CLEANER. In cases of salts use HARD REMOVER. For additional information, refer to the relative Technical Data Sheets of the products.

Recommendations

- Do not apply in surfaces that are not dry
- Do not apply the varnish on surfaces where rising humidity is possible or present
- Do not apply when the temperature is lower than +12°C and the relative humidity of the atmosphere exceeds 65%, or when there is a possibility of rain and wet weather, before the varnish is completely dry
- Do not apply PLANOFINISH PU 2KS upon fresh concrete if at least 4 weeks haven't passed and without holding humidity measurements
- Two components of PLANOFINISH PU 2KS are in proportion so never mix partially the two components. In some cases, if necessary, diluting can only be done with a compatible solvent such as NOVATHINNER PU.
- Do not apply PLANOFINISH PU 2KS upon old varnishes and dusty or dirty surfaces. Remove dust and dirt immediately before application. In any case, the surface should be well wiped off and, if necessary, be sanded before application.
- Always use appropriate and clean tools.
- When applying in swimming pools chemical over-consumption should not occur. This applies both to the operation period and to the cleaning of the pool when it is empty.
- In swimming pools or areas with humidity if the protective layer of PLANOFINISH PU 2KS isn't continuous, moisture may penetrate underneath and then the surface will become discolored and we may also have detachments.
- Do not apply PLANOFINISH PU 2KS in excess quantity, in such a case it cannot be polymerized properly and doesn't set properly.
- All measurements and waiting time refer to surface temperature of +23°C and residual humidity of 50%. Variations on the above may after waiting times or application process.
- For daily maintenance or cleaning of surfaces treated with PLANOFINISH PU 2KS, use suitable professional cleaners such as ALCALINE CLEANER, NEUTRAL CLEANER or HARD REMOVER. Avoid using highly acidic products and, in cases of doubt, always test before application.
- PLANOFINISH PU 2KS is a solvent-based varnish recommended mainly for external area applications. In any case however any precautions required of the use of solvent-based materials should be applied.

Consumption

Consumption is 250 – 375 ml/m² for application in 2 - 3 coatings depending on the application.

Cleaning

Buckets, tools, coatings etc. can be cleaned with solvent if the mix is still fresh. Once dried cleaning can be done only by mechanical means or strong corrosives

Storage

PLANOFINISH PU 2KS remains stable for at least 12 months in the original sealed packaging stored in a dry place protected from humidity, frost and direct sunlight exposure in temperature between +5°C and +30°C.

Packaging

Metallic containers of 1 & 5 L (A+B) in predetermined mixing ratio.

Safety Instructions

For information and instructions regarding disposal and safe handling, users should refer to the latest Safety Data Sheet of the product containing ecological, toxicological and other safety-related data.

Legal notes

The technical data and recommendations contained or listed in this leaflet are the result of laboratory measurements, of our current knowledge and experience. All the above-mentioned information and specifications should in any case be considered as indicative, as they may differ from each other. The Company makes every effort to ensure the accuracy of the information provided herein. Product specifications, prices and availability are subject to change without notice and may differ from those shown.

In practice, variations in materials, substrates and on-site implementation conditions are such that no warranty can be given or implied, as to the merchantability or suitability of the materials for a particular purpose and for the exact conditions of each project. Anyone interested of using the product must be sure beforehand that the product is suitable for the intended use and in any case, the user is solely responsible for any consequences due to the use of the product. Among other things, the Company is not responsible for any normal wear or tear from environmental or other inappropriate conditions. We reserve the right to revise or change the data herein without prior notice.

Restrictions and disclaimers apply to the extent permitted by applicable law. The Company has a Technical Support Department, which is the only one responsible for providing technical advice and solutions to deal with problems. Requests to the Technical Support Department are addressed and answered, only in writing.

For the latest and a valid version of the Technical Data Sheet, the user of the material must refer to our website www.novamix.gr or directly to the QR Code of the product.



DOMOCHEMICAL S.A.
40 Papanikoli str.
Chalandri, 15232, Athens
T +30 210 68 93 953
F +30 210 68 94 571
novamix@novamix.gr