

Teak oil

Wood Penetration Oil



Mixture of modified natural oils combined with wax. It can be used to refresh and preserve wooden surfaces like teak, oregon, rosewood, mahogany etc. as well as for all bare woods. It is suitable for interior and exterior use. It penetrates deeply through the wood pores preventing the penetration of water and enhances its natural beauty. Refresh, preserve and protect the wood from the strong sunlight and humidity.

- **Penetration oil from mixture of modified natural oils enriched with wax**
- **Refresh, preserves and protect the wood from the strong sunlight and humidity**

COLOURS

Available colourless.

PACKAGING

| | |
|------------|--------|
| Colourless | 750 mL |
|------------|--------|

SPREADING RATE

14 - 16 m²/L per coat on previously prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/h** "Binding primers", Type **SB**): **750 g/L**. This product contains maximum **450 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be smooth, clean, dry, free from grease, resins or old varnishes.

APPLICATION

Stir well before use. Apply one coat by brush or piece of cloth without dilution. Wipe excess material after 5 minutes with a dry cloth. Apply a second coat for tough wood or when wood is exposed to adverse weather conditions. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch dry after 2-3 hours and can be recoated after 2 days. Drying time depends on weather conditions (humidity and temperature).

Clean rollers, brushes, floor stains, etc. with Brush Solvent T 300 and then with soapy water or detergent.



TECHNICAL CHARACTERISTICS


| | |
|-----------|----------------------------------|
| Viscosity | 15 - 30 sec (FORD CUP #4, 25° C) |
| Density | 0,85 ± 0,02 Kg/L (ISO 2811) |

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr