

Chassis coat

Anticorrosive solvent-based paint



It is a quick drying, durable solvent-based paint. It provides great protection against corrosion and excellent fastness to grease, lubricating oils and petroleum compounds. It offers great adhesion, elasticity and has great impact resistance. Suitable for painting chassis of cars and metallic surfaces.

- **Fast drying primer - top coat**
- **For cars' chassis**
- **Diluted with White Spirit**

COLOURS

Available in white, grey, black and brown.

PACKAGING

Shades	750 mL	2.5L
--------	--------	------

SPREADING RATE

12 - 14 m²/L per coat on properly prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/i** "One-pack performance coatings", Type **SB**): **500 g/L**. This product contains maximum **495 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be cleaned with Brush Solvent T 300, be smooth and dry, free from dust, grease or rust and sanded.

Glossy metallic surfaces (aluminum, galvanized steel etc) should be first coated with Primer for Glossy Surfaces or Wash Primer.

APPLICATION

Stir well before use. Apply two coats by roller or brush diluted up to 5% with Brush Solvent T 300 or airless spray gun diluted up to 5% with Spray Gun Solvent T 350. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch dry after 1-2 hours and can be recoated after 20-24 hours. Drying time depends on weather conditions (humidity and temperature).

Clean rollers, brushes, floor stains, etc. with Brush Solvent T 300 and then with soapy water or detergent. Use Spray Gun Solvent T 350 to clean spray guns.



TECHNICAL CHARACTERISTICS

Viscosity	80 ± 5 KU (ASTM D 562, 25°C)
Density	1,35 ± 0,02 Kg/L (ISO 2811) for white
Gloss	40-60 units @ 60° (ISO 2813)

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr