

Verolac

High durability gloss enamel paint



It is very durable, gloss enamel based on alkyd resins, suitable for interior and exterior use on metallic surfaces. It forms a hard film that retains its gloss and shade unchanged, even if exposed to adverse weather conditions or washed.

Due to its special formulation is excellent anticorrosion finish for all kinds of metallic surfaces. Offers high hiding power, excellent working and levelling properties, providing protection and decoration.

- Gloss tough enamel
- High quality and durability

COLOURS

Available in white, black and 48 more shades (refer to colour card).

PACKAGING

Shades	180 mL	375 mL	750 mL	2.5L	5 L
--------	--------	--------	--------	------	-----

SPREADING RATE

14 - 16 m²/L per coat on properly prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/i** "One-pack performance coatings", Type **SB**): **500 g/L**. This product contains maximum **495 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be cleaned with Brush Solvent T 300, be smooth and dry, free from dust, grease or rust and sanded.

Metallic surfaces should be coated with an anticorrosive primer (Anti-Rust Primer, Minio New Type or Metal Primer).

Glossy metallic surfaces (aluminum, galvanized steel etc) should be first coated with Primer for Glossy Surfaces or Wash Primer.

APPLICATION

Stir well before use. Apply two coats by roller or brush diluted up to 5% with Brush Solvent T 300 or airless spray gun diluted up to 5% with Spray Gun Solvent T 350. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch dry after 2-3 hours and can be recoated after 20-24 hours. Drying time depends on weather conditions (humidity and temperature). Allow at least 30 days before cleaning and washing newly painted surfaces with Verolac.

Clean rollers, brushes, floor stains, etc. with Brush Solvent T 300 and then with soapy water or detergent. Use Spray Gun Solvent T 350 to clean spray guns.



TECHNICAL CHARACTERISTICS

Viscosity	70 ± 5 KU (ASTM D 562, 25°C)
Density	1,21 ± 0,02 Kg/L (ISO 2811) for white
Gloss	> 90 units @ 60° (ISO 2813)

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr