

Neodur[®] FT Clear

Transparent, 2-component, aliphatic polyurea varnish ideal for the waterproofing of tiled surfaces

Description of the product

Neodur[®] FT Clear is a technologically advanced, transparent, fast curing, brushable elastic polyaspartic varnish. It is ideal for waterproofing roofs and balconies that have been fitted with tiles. It offers high mechanical strength and long-term resistance to UV radiation without yellowing.

Properties

- High resistance to abrasion and mechanical stress
- Zero water absorption
- Highly resistant to UV radiation. It does not yellow even after many years
- Crack bridging properties
- Fast drying
- Certified with CE (EN 1504-2)

Technical characteristics

Appearance	Transparent
Density (25°C)	1,04±0,01g/cm ³
Mixing Ratio (weight prop.)	1:1
Consumption	700gr/m ² (for 2 layers)
Pot life (+25°C)	30 min
Drying time (+25°C)	5 hours
Total hardening (+25°C)	7 days
Service Temperature	-35°C min / +60°C max
Elongation (ASTM D412, +25°C)	200%
Surface humidity content	<4%
Hardness Shore D (EN ISO 868:2003/ASTM 2240)	25
Tensile Strength (ASTM D412, +25°C)	22MPa
Abrasion resistance	80mg (Taber test CS 10/1000/1000, ASTM D4060)

Neodur[®] FT Clear

Instructions for use

Surface preparation: The surface under the tiles should be dry. In case of moisture beneath the tiles, ventilators should be fitted before the application. The surfaces must be rough (not smooth) and thoroughly dry, free from dust, dirt, greasy and oily substances. In case of glossy tiles, it is necessary to grind the tiles and remove the glazy film. For mat tiles, the surface must be treated with **Neosil[®] Bond** in order to improve the adhesion of the following material. For applications where the tile grout is fresh (less than 1 year), it is necessary to apply **Neodur[®] Polyurea M** as a primer, diluted with **Neotex[®] PU 0413** (50-60%) with a consumption of 50 gr/m². If the tiles are not newly installed, then after treatment with **Neosil[®] Bond**, **Neodur[®] FT Clear** can be applied directly in two layers.

Application: After very good stirring of the components A & B in the appropriate ratio, the mixture is applied onto the surface and spread thoroughly by brush or roller.

Special notes

- **Neodur[®] FT Clear** should not be applied when the temperature is below + 5°C.
- In places where there are moving joints and at the entrance, ready expansion joint cover profiles should be used. Also pay attention to the details and mountings where there are gutters and metal grates.
- The surface should be dry during application and protected from rising moisture.
- **Neodur[®] FT Clear** is not suitable for the production of stone carpets.

Cleaning of tools

Immediately after application with solvent **Neotex[®] 1021**.


Packing

Set (A+B) 8kg, 2kg

Storage

1 year if kept unopened in its original package, protected from frost and sunlight.

Neodur[®] FT Clear



1922

NEOTEX A.E.B.E
B. Μοίρα, Θέση Ξηροπήγαδο, Τ.Θ. 2315
19600, ΒΙ.ΠΑ Μάνδρα Αττικής

NEOTEX S.A
V. Moira str., P.O. Box 2315
GR 19600 Industrial Area Mandra, Athens, Greece

19

1922-CPR-0386

Dop No/4950-46

EN 1504-2

Neodur[®] FT Clear

Σύστημα προστασίας επιφανειών σκυροδέματος

Surface Protection System for Concrete

Επικάλυψη

Coating

Διαπερατότητα υδρατμών /Water Vapour
Permeability

Κατηγορία/Class I

Αντοχή αποκόλλησης /Adhesion Strength

$\geq 1.5\text{N/mm}^2$

Τριχοειδής απορρόφηση και
υδατοπερατότητα/ Capillary Absorption

$W < 0.1\text{Kg/m}^2\text{h}^{0.5}$

Διαπερατότητα σε CO₂/Permeability to CO₂

$S_D > 50\text{m}$

Αντίδραση στη φωτιά/Reaction to Fire

Ευρωκατηγορία F/Euroclass F

Επικίνδυνες ουσίες/Dangerous Substances

Σύμφωνα με 5.3/Comply with 5.3