

SILVER

Aluminium Paint For Metallic Surfaces



Aluminium paint Silver is suitable for the protection of metallic surfaces such as stovepipes, chimneys etc. It is resistant to high temperatures (up to 200°C), adverse weather conditions and daylight.

- Aluminium paint for ~ 200°C
- Protection of metallic surfaces

COLOURS

Available in silver shade.

PACKAGING

Silver	180 mL	375 mL	750 mL
--------	--------	--------	--------

SPREADING RATE

12 - 14 m²/L per coat on properly prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/i** "One-pack performance coatings", Type **SB**): **500 g/L**. This product contains maximum **499 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be cleaned with Brush Solvent T 300, be smooth and dry, free from dust, grease or rust and abraded.

APPLICATION

Stir well before use. Apply one coat by roller, brush or airless spray gun without dilution and without primer. After application, 24 hours should elapse before warming the painted surface. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch dry after 2-3 hours and can be recoated after 24 hours. Drying time depends on weather conditions (humidity and temperature).

Clean rollers, brushes, floor stains, etc. with Brush Solvent T 300 and then with soapy water or detergent. Use Spray Gun Solvent T 350 to clean spray guns.



TECHNICAL CHARACTERISTICS

Viscosity	< 30 sec (FORD CUP#4, 20°C)
Density	0,95 ± 0,02 Kg / L (ISO 2811)

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr