

EUMARIA ANTIFOULING ULTRA MULTI

High strength self-polishing organotin-free antifouling paint. Contains copper (I) thiocyanate and specific controlled release biocides, protects submerged areas against bacteria, algae, seaweed, shellfish and generally adherent organisms for 2-5 years depending on conditions. Ideal for hulls made of polyester, wood, steel and aluminum or light alloys, cruising at speeds of 18-32 knots, cruising at speeds of 18-32 knots with long idle periods.

SHADES	White, grey, light blue and black.
FINISH	Flat
SPECIFIC GRAVITY	1,34 – 1,56 Kg/L (depending on shade)
VOLUME SOLIDS %	~50%
VOC	<500g/L
UNIT SIZE	750mL, 2.5L, 20L.
SPREADING RATE	Approximately 8-10 m ² /L per coat.
DRYING	For complete drying require 16 hours at 10°C, 8 hours at 15°C, 4 hours at 25°C, 3 hours at 35°C. Painted surfaces can be safely used by humans and animals after drying time.
RECOATABILITY TIME	2-3 coats of 120 microns wet film thickness are required. Recoat after the previous layer is completely dried. (Consult the detailed Eumaria Technical Guide).
SURFACE PREPARATION	Surface must be completely clean and dry at the time of application and the temperature must be above the dew point to avoid condensation of moisture. Make sure there is adequate ventilation during application and drying. To paint over old antifouling, abrade surface, remove dirt, algae, seaweed shellfish etc. and rinse thoroughly with fresh water at high pressure. If priming is required (old antifouling unknown or in poor condition) use Eumaria Vinyl Primer one Component.
THINNING	Ready to use. If required, thin up to 10% with Eumaria Thinner 200.
APPLICATION	Apply by roller, brush or airless spray.
CLEANING OF TOOLS	Tools must be cleaned immediately after use with Eumaria Thinner 200.
LAUNCHING	After the final coat is completely dry. But it can be delayed for a few days at a low temperature - or when it is not exposed to sunlight - up to two months without affecting the antifouling properties.
STORAGE	Maximum storage time 2 years from the production date. Keep containers closed in a cool, dry, well ventilated place, away from solar radiation in temperatures between 5°C and 38°C and/or relative humidity less than 80%.
NOTE	Stir well before use. Avoid application in direct sunlight and temperatures below 10°C, above 35°C and / or relative humidity above 80%.
HEALTH, SAFETY & ENVIRONMENTAL ISSUES	Consult the Safety Data Sheet.