

Primer

Water-based 100% acrylic



Semi-transparent water-based primer of 100% acrylic resins. It is used as an undercoat for Vitex's water-based paints (emulsion, acrylic, cement paints, relief, etc.). It is very easy to apply and has high spreading rate. It improves the appearance, hiding power and weather resistance of the final coat. It is a suitable primer for alkaline surfaces as well because it impregnates and stabilizes them. Virtually odourless during its application because it does not contain ammonia.

- 100% acrylic
- Excellent adhesion
- Improves the final coat

COLOURS

Available in semi-transparent.

PACKAGING

Semi-transparent	750 mL	3 L	10 L
------------------	--------	-----	------

SPREADING RATE

18 - 20 m²/L per coat on properly prepared surfaces, depending on thinning and surface absorption.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/h** "Binding Primers", Type **WB**): **30 g/L**. This product contains maximum **6 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be smooth, clean and dry, free from grease, dust, loose or flaking paint.

APPLICATION

Stir well before use. Apply one coat by roller, brush or airless spray gun diluted up to 300-400% with water. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch-dry after 15-30 minutes and can be recoated after 4-6 hours with Vitex's emulsion or acrylic paints. Drying time depends on weather conditions (humidity and temperature).

Tools must be cleaned immediately after use with water and if needed with soapy water or a detergent.



TECHNICAL CHARACTERISTICS

Viscosity	70 ± 5 KU (ASTM D 562, 25° C)
Density	1,03 ± 0,02 Kg / L (ISO 2811)

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr