

Acrylic Putty



White water-based acrylic putty for interior and exterior use. It exhibits excellent resistance to adverse weather conditions, damp, alkalinity and is suitable for tiling and coating of plaster, concrete, wood and for decorative applications. It has excellent working properties and dries fast without cracking. It is easy to sand and gives a smooth surface.

- For interior and exterior use
- Excellent filling, easy to sand and gives a smooth surface

COLOURS

Available in white.

PACKAGING

White	400 gr	800 gr	5 Kg
-------	--------	--------	------

SPREADING RATE

2 - 3 m²/Kg per coat on properly prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/g** "Primers", Type **WB**): **30 g/L**. This product contains maximum **29 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces must be clean, dry and smooth, free from dust, grease, loose material.

APPLICATION

Apply the product using a spatula without dilution. After 2-3 hours, the product is rubbed with sandpaper and surface is paintable with any emulsion or acrylic water-based or solvent-based coating of Vitex. Do not apply at temperature below 5°C, above 35°C and/or relative humidity above 80%.

It is touch dry in 30 minutes and can be recoated after 3-4 hours, depending from absorption of the surface. Drying time depends on weather conditions (humidity and temperature).

Tools must be cleaned immediately after use with water and if needed with soapy water or a detergent.



TECHNICAL CHARACTERISTICS

Viscosity	520.000 ± 150.000 cP (BROOK-FIELD, 25°C)
-----------	--

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr