Technical leaflet

MARMOCRET 1



One-layer plaster

Description

MARMOCRET 1 is a pre-mixed, one-layer plaster (skim coat). It only requires the addition of water. It replaces the two final layers (basic and finishing coat) of common plastering works, applied in a maximum thickness of 3 cm.

- It offers high adhesion to the substrate and very good workability.
- It simplifies and accelerates the application.
- It is ideal for application with plastering machine.
- It maintains a standard quality.
- It provides the construction with excellent vapor permeability.
- It is suitable for indoor and outdoor applications.

It is classified as type OC CS II, W1 mortar according to EN 998-1.

Fields of application

It is used in plastering works. Suitable for indoor and outdoor use and wherever it is required to work fast.

Technical data

Form: cementitious powder

Color: grey, white

Particle size: up to 1.3 mm

Water demand: 5.70-6.30 l/30 kg bag

Bulk density

of dry mortar: $1.50 \pm 0.10 \text{ kg/l}$

Bulk density

of fresh mortar: $1.65 \pm 0.10 \text{ kg/l}$ Compressive strength: $3.00 \pm 0.50 \text{ N/mm}^2$ Flexural strength: $1.30 \pm 0.20 \text{ N/mm}^2$ Adhesion: 0.30 N/mm²

(28 days)

Capillary water

absorption: $\leq 0.4 \text{ kg/m}^2 \text{ min}^{0.5}$

Thermal conductivity

coefficient ($\lambda_{10,dry}$): $\leq 0.47 \text{ W/(m K)}$

for P=50%

Water-vapor diffusion

coefficient (µ): 12

Pot life: $4 \text{ h at } +20^{\circ}\text{C}$

Maximum layer

thickness: 30 mm

Directions for use

1. Substrate preparation

The substrate should be stable, free of dust, oily or loose materials etc. and should be thoroughly dampened. A bonding spatterdash (rough cast) with MARMOCRET-BOND should be applied on the surface, before the application of MARMOCRET 1. After the bonding spatterdash has dried, MARMOCRET 1 may be applied.

2. Application

MARMOCRET 1 is added into clean water under continuous stirring, until the mortar formed has the required workability. The plaster is applied by hand, using a float, trowel or plastering machine. The plaster is then smoothed by hand, using a spongy float, after it has sufficiently set. Working time depends on substrate absorptivity, ambient temperature and workability of the mixture.

Consumption

Approx. 15 kg/m²/cm of plaster thickness.

MARMOGRET 1



Packaging

MARMOCRET 1 is supplied in 30 kg paper bags.

Shelf-life - Storage

12 months from production date, if stored in original, unopened packaging, in places protected from moisture and frost.

Remarks

- Temperature during application should be at least +5^oC.
- In hot weather, MARMOCRET 1 should be watered after application, to be protected from water loss.
- MARMOCRET 1 contains cement and reacts with water, forming an alkaline solution, so it is classified as irritant.
- Consult the directions for safe use and precautions written on the package.



ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece

09

EN 998-1

One coat rendering mortar (OC) for external use

Reaction to fire: Class A1

Adhesion after weathering cycles: 0.3 N/mm²

- **FP**: B

Water absorption: W1

Water permeability after weathering cycles:

 $\leq 1 \text{ cm/m}^2$

Water vapor diffusion coeff.: µ 12

Thermal conductivity: $(\lambda_{10,dry})$ 0.47 W/mK

Durability (against freeze/thaw): evaluation based on provisions valid in the intended place of

use of the mortar

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road, P.O. BOX 1043, 570 03 Ag. Athanasios, Greece, Tel.: +30 2310 576 000, Fax: +30 2310 722 475

www.isomat.net e-mail: info@isomat.net





