

Velatura

Alkyd-based undercoat for enamels



White, matt, solvent-based alkyd undercoat. It provides a perfect substrate for enamels, especially when applied to wooden surfaces. Produces an excellent surface for finishing with enamels (Verolac, Platinum, Aquavit). It offers hiding power and whiteness, while at the same time it combines good brushability, excellent levelling, easy sanding and resistance to sagging.

- High hiding power
- Excellent brushability, leveling and easy sanding

COLOURS

Available in white.

PACKAGING

White	375 mL	750 mL	2.5 L	5 L
-------	--------	--------	-------	-----

SPREADING RATE

16 - 18 m²/L per coat on properly prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/g** "Primers", Type **SB**): **350 g/L**. This product contains maximum **348 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be smooth, clean and dry, free from grease, dust, loose or flaking paint.

On new wooden surfaces scrape off the knots and then apply wood preservative Diaxyl Decor.

To fill any cracks or holes use Acrylic Putty.

APPLICATION

Stir well before use. Apply one or two coats by roller or brush diluted up to 3% with Brush Solvent T 300 or airless spray gun diluted up to 3% with Spray Gun Solvent T 350. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch dry after 2-3 hours and can be recoated after 16-18 hours. When the coating is thoroughly dry, use an appropriate abrasive paper to produce a smooth surface, remove the dust and apply any Vitex's enamel water based or solvent based paint. Drying time depends on weather conditions (humidity and temperature).

Clean rollers, brushes, floor stains, etc. with Brush Solvent T 300 and then with soapy water or detergent. Use Spray Gun Solvent T 350 to clean spray guns.



TECHNICAL CHARACTERISTICS

Viscosity	90 ± 10 KU (ASTM D 562, 25°C)
Density	1,48 ± 0,02 Kg / L (ISO 2811)

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr