

Lussolac (w)

Water based wood varnish



Water-based, odourless, wood varnish based on a combination of self-crosslinking acrylic and polyurethane resins for exterior and interior use on wooden surfaces. It has excellent working properties and good durability even if exposed to adverse weather conditions, such as intense sunshine or increased humidity.

- **Protects and decorates interior and exterior wooden surfaces**
- **Durable to intense sunshine and humidity**

COLOURS

Available colourless in gloss, satin or mat finish.

PACKAGING

Colourless	750 mL	2.5L
------------	--------	------

SPREADING RATE

12-14 m²/L per coat on properly prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/e** "Interior/exterior trim varnishes and woodstains, including opaque woodstains", Type **WB**): **130 g/L**. This product contains maximum **99 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be smooth, clean, dry, free from grease or rosins and abraded.

On new wooden surfaces apply preservative Diaxyl Decor water-based.

APPLICATION

Stir well before use. Apply one or two coats by roller, brush or spray gun diluted up to 10% with water. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch-dry after 1-2 hours and can be recoated after 6-8 hours. Drying time depends on weather conditions (humidity and temperature).

Tools must be cleaned immediately after use with water and if needed with soapy water or a detergent.



TECHNICAL CHARACTERISTICS

Viscosity	80 ± 10 KU (ASTM D 562, 25° C)
Density	1,05 ± 0,02 Kg/ L (ISO 2811)
Gloss	Gloss: > 80 units @ 60° Satin: 20 - 30 units @ 60° Mat: < 15 units @ 60° (ISO 2813)

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr