

# Lussolac

## Solvent-based wood varnish



Solvent-based polyurethane varnish (one component) for indoors and outdoors wooden surfaces. It has excellent application properties, as well as very good elasticity and hardness. The polyurethane resin provides excellent durability even if exposed to adverse weather conditions, while the UV filters protect wood from the damaging effects of sunrays.

- Polyurethane wood varnish
- With UV filters to protect wood from the damaging effects of sunrays

### COLOURS

Available colourless in gloss, satin and mat finish and in 11 glossy ready shades.

### PACKAGING

Gloss colourless	180 mL	750 mL	2.5L
Satin and mat colourless	750 mL	2.5L	
Glossy shades	180 mL	750 mL	

### SPREADING RATE

12 - 16 m<sup>2</sup>/L per coat on properly prepared surfaces.

### VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/e** "Interior/exterior trim varnishes and woodstains, including opaque woodstains", Type **SB**): **400 g/L**. This product contains maximum **399 g/L** VOCs (ready for use product).

### SURFACE PREPARATION

Surfaces should be smooth, clean and dry, free from grease or resins and abraded.

On new wooden surfaces apply preservative Diaxyl Décor.

### APPLICATION

Stir well before use. Apply one or two coats by roller or brush diluted up to 5% with Brush Solvent T 300 or airless spray gun diluted up to 5% with Spray Gun Solvent T 350. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch dry after 3-4 hours and can be recoated after 20-24 hours. Drying time depends on weather conditions (humidity and temperature).

Clean rollers, brushes, floor stains, etc. with Brush Solvent T 300 and then with soapy water or detergent. Use Spray Gun Solvent T 350 to clean spray guns.



### TECHNICAL CHARACTERISTICS

Viscosity	55 ± 10 KU (ASTM D 562, 25° C)
Density	0,95 ± 0,02 Kg / L (ISO 2811)
Gloss	Gloss: > 90 units @ 60° (ISO 2813) Satin: 20 - 40 units @ 60° (ISO 2813) Mat: < 15 units @ 60° (ISO 2813)

### STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

### SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00  
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00  
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr