

EUMARIA VINYL PRIMER ONE COMPONENT

Chlorinated vinyl one component primer with aluminum flakes. Suitable barrier/sealer coat over incompatible or unknown antifouling. As an intermediate/sealer coat between epoxy primer and topcoat or Antifouling.

SHADES	Silver.
FINISH	Flat.
SPECIFIC GRAVITY	~1,19 - 1,23 Kg/L.
VOLUME SOLIDS %	~45%
VOC	EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category A/i "One-pack performance coatings", Type SB): 500 g/L. This product contains maximum 499 g/L VOCs (ready for use product).
UNIT SIZE	750mL, 2.5L, 20L.
SPREADING RATE	8-12 m ² /L per coat on properly prepared surfaces
DRYING	Touch dry after 2 h @ 5°C, 1 h @ 15°C 40min @ 25°C, 15min @ 35°C (80-120µm wet film thickness).
MINIMUM RECOATABILITY TIME	2 h @ 5°C, 2 h @ 15°C 1h @ 25°C, 40min @ 35°C (80-120µm wet film thickness).
SURFACE PREPARATION	Surfaces must be clean and dry and the temperature must be above the dew point to avoid condensation of moisture. For use over old antifouling, remove dirt, algae, seaweed shellfish etc. and wash thoroughly with fresh water at high pressure.
THINNING	Ready for use. If required, dilute 5% - 10%. Use Eumaria Thinner 200.
APPLICATION	Apply by roller, brush or airless spray gun.
CLEANING OF TOOLS	Tools must be cleaned immediately after use with Eumaria Thinner 200.
APPLICATION – NUMBER OF LAYERS	Consult the detailed Technical Eumaria Guide.
STORAGE	Keep containers closed in a cool, dry, well ventilated place, away from solar radiation in temperatures 5°C and 38°C and/or relative humidity less than 80%.
NOTE	Do not apply in direct sunlight and temperatures below 10°C, higher than 35°C and / or relative humidity above 80%. In confined spaces, make sure there is adequate ventilation during application and drying.
HEALTH, SAFETY & ENVIRONMENTAL ISSUES	Consult the Safety Data Sheet.