

Vitosin

Insulating solvent-based primer



White mat, solvent-based, multi-purpose primer based on thermoplastic acrylic resins. Owing to its unique formula, it isolates and covers surfaces stained with smoke, smog, grease, moisture, mildew, etc., without allowing them to reappear. Due to its long-lasting whiteness, its exceptional resistance to water vapour and mildew is ideal for insulating surfaces covered with water paints or distempers (lime wash or ceiling white). It is also used as an undercoat for Vitex's water-based paints and as a final paint for ceilings. It provides great hiding power, premium quality, superior durability, as well as excellent spreading rate and adhesion to masonry surfaces, plaster, wood, etc.

- For surfaces stained with smoke, smog, grease, moisture, mildew etc
- Ideal for insulating surfaces covered with water paints or distempers
- Excellent adhesion

COLOURS

Available in white.

PACKAGING

Cans	750 mL	2,5 L	10 L
------	--------	-------	------

SPREADING RATE

7 - 9 m²/L per coat on properly prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/h** "Binding Primers", Type **SB**): **750 g/L**. This product contains maximum **499 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be smooth, clean and dry, free from grease, dust, loose or flaking paint.



APPLICATION

Stir well before use. Apply one or two coats by roller or brush diluted up to 5% with Brush Solvent T 300 or airless spray gun diluted up to 5% with Spray Gun Solvent T 350. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%. It is touch dry after 1-2 hours and can be recoated after 24 hours or after 4-6 hours for coated with Vitex's emulsion or acrylic paints. Drying time depends on weather conditions (humidity and temperature). Clean rollers, brushes, floor stains, etc. with Brush Solvent T 300 and then with soapy water or detergent. Use Spray Gun Solvent T 350 to clean spray guns.

TECHNICAL CHARACTERISTICS

Viscosity	90 ± 5 KU (ASTM D 562, 25° C)
Density	1,37 ± 0,02 Kg / L (ISO 2811)

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr