

## Neotex® PE-6/TC

### Unsaturated thixotropic polyester preaccelerated

<b>Fields of application</b>	<ul style="list-style-type: none"> <li>• Constructions - repairs of reinforced plastics (e.g. yacht, tanks, sprayers, molds)</li> <li>• Plasticization (e.g. boats, car parts, roofs)</li> <li>• Waterproofing (e.g. pendants, tanks)</li> </ul>
------------------------------	--

#### Technical Characteristics (non reinforced)

<b>Density</b>	1,10g/cm <sup>3</sup>
<b>Dosage (by weight)</b>	<b>MEKP-50</b> Catalyst 10 to 20g per kg of polyester <b>NEOTEX® PE-6/TC</b>
<b>Viscosity</b>	5.5 – 6.5 dPa.s
<b>Solid content</b>	56 – 60%
<b>Volumetric shrinkage</b>	7%
<b>Tensile Modulus ISO 527 (1999)</b>	3715Mpas
<b>Tensile strength ISO 527 (1999)</b>	57Mpas
<b>Elongation</b>	2,3%
<b>Flexural strength ISO 178 (2003)</b>	98Mpa
<b>Flexural modulus ISO 178 (2003)</b>	3630
<b>Thermomechanical properties HDT ISO 75-2 A (1999) (°C)</b>	64 (2hrs at 120°C)
<b>Hardening time at +25° C</b>	10 to 30 minutes, depending on ambient temperature and catalyst rate
<b>consumption</b>	1kg/m <sup>2</sup> per layer with reinforcement

#### Instructions for use

**Surface preparation:** The substrate should be clean, dry and free from dust, oil, grease, or any poorly adhering material. Use compressed air, any suitable mechanical means, or washing with solvents. The surface is either forced dry by blowing hot air or can dry naturally. To improve the adhesion on concrete and metal surfaces, it is recommended to use **Neotex PU® Primer**.

**Application:** Use fiberglass, between the 2 coatings, while the 1st is still wet. Previous work is repeated until the thickness required of construction or repair is achieved. If needed more fluidity the mixture diluted 5% with **Styrene**.

**Gelcoat (Topcoat)** can be applied as a final layer.

#### Notes

- *Application Conditions:* Minimum application temperature: + 12°C
- Due to the quick curing rate and drying time, it is suggested to thoroughly evaluate the product before using. Mix as

ATHENS: V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482  
THESSALONIKI: Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

## Neotex<sup>®</sup> PE-6/TC

much material as you can apply within its pot life.

<b>Cleaning of tools</b>	Clean all tools and application equipment with <b>Acetone</b> .
<b>Packing</b>	1kg, 3kg, 6kg, 20kg and 225kg
<b>Auxiliary Materials</b>	Transparent polyester suitable for molding (eg statues, decorations, frames, trinkets)
<b>Storage stability</b>	6 months, stored in its initial, sealed package, at +5°C to +25°C, protected from sunlight, moisture and frost, away from heat sources, flames and sparks.
<b>Safety Precautions</b>	See Safety Data Sheets.