

Metal primer

Primer for metallic surfaces



Primer based on hard, quick-drying alkyd resins. It provides the perfect substrate for enamels, especially when used on metallic or wooden surfaces. It can also be used for wall pretreatment as it insulates and covers patches, spots, stains, etc. Produces an excellent finish for coating with any type of enamel paint, offering exceptional adhesion, whiteness and hiding power. At the same time, it combines good brushability, excellent leveling and easy sanding.

- High spreading rate
- Anticorrosive protection

COLOURS

Available in white and grey.

PACKAGING

Shades	375 mL	750 mL	2.5L	5 L	10 L
--------	--------	--------	------	-----	------

SPREADING RATE

16 - 18 m²/L per coat on properly prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/i** "One-pack performance coatings", Type **SB**): **500 g/L**. This product contains maximum **495 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be cleaned with Brush Solvent T 300, be smooth and dry, free from dust, grease or rust and abraded.

APPLICATION

Stir well before use. Apply one or two coats by roller or brush diluted up to 5% with Brush Solvent T 300 or airless spray gun diluted up to 5% with Spray Gun Solvent T 350. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch dry after 45-60 minutes and can be recoated after 20-24 hours. When the coating is thoroughly dry, sand with an appropriate abrasive paper to produce a smooth surface, remove the dust and then apply any Vitex's enamel water based or solvent based paint. Drying time depends on weather conditions (humidity and temperature).

Clean rollers, brushes, floor stains, etc. with Brush Solvent T 300 and then with soapy water or detergent. Use Spray Gun Solvent T 350 to clean spray guns.



TECHNICAL CHARACTERISTICS

Viscosity	80 ± 5 KU (ASTM D 562, 25° C)
Density	1,46 ± 0,02 Kg/L (ISO 2811)

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr