

Martelite

Hammer-effect paint



Alkyd hammer-effect solvent-based paint suitable for the protection and decoration of metallic surfaces. It provides strong adhesion, quick drying and great durability to adverse weather conditions. It has good working and levelling properties and can be applied directly onto metal without using an undercoat. It gives an excellent hammer-effect finish.

- Protection and decoration of metallic surfaces
- Great durability

COLOURS

Available in 13 colour card shades.

PACKAGING

Shades	750 mL	2.5L
--------	--------	------

SPREADING RATE

8 - 10 m²/L per coat on properly prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/i** "One-pack performance coatings", Type **SB**): **500 g/L**. This product contains maximum **499 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be cleaned with Brush Solvent T 300, be smooth and dry, free from dust, grease or rust and sanded.

Glossy metallic surfaces (aluminum, galvanized steel etc) should be first coated with Primer for Glossy Surfaces or Wash Primer.

APPLICATION

Stir well before use. Apply two coats by roller, brush or airless spray gun diluted up to 5% with Spray Gun Solvent T 350. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch dry after 20-30 minutes and can be recoated after 16-20 hours. Drying time depends on weather conditions (humidity and temperature).

Tools must be cleaned immediately after use with Spray Gun Solvent T 350.



TECHNICAL CHARACTERISTICS

Viscosity	65 ± 10 KU (ASTM D 562, 25°C)
Density	0,98 ± 0,03 Kg /L (ISO 2811)

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr