

Direct - 1

Anticorrosive paint



It is a durable, glossy, quick-drying, anticorrosive paint suitable for painting onto either old or newly painted or rusted metallic surfaces, without pre-applying any primer. It provides great durability, strong adhesion, elasticity and long-term protection against corrosion. It has good working and levelling properties without leaving any brush and/or joint paint marks.

- Direct application on rust without primer
- Great durability

COLOURS

Available in white, black and 10 more shades (refer to colour card).

PACKAGING

Shades	750 mL	2.5L
--------	--------	------

SPREADING RATE

4 - 8 m²/L per coat on properly prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/i** "One-pack performance coatings", Type **SB**): **500 g/L**. This product contains maximum **499 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be cleaned with Brush Solvent T 300, be smooth and dry, free from dust, grease or rust and sanded.

Glossy metallic surfaces (aluminum, galvanized steel etc) should be first coated with Primer for Glossy Surfaces or Wash Primer.

APPLICATION

Stir well before use. Apply two coats by short hair roller or brush without dilution or airless spray gun diluted up to 15% with Spray Gun Solvent T 350. Paint quickly and carefully to ensure proper coating of the surface and obtain complete isolation from humidity, especially in difficult to paint spots, such as corners and edges. Best protection is provided with a 100 µm dry film thickness, which is formed by applying two coats of Direct-1. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch dry after 30-60 minutes and can be recoated after 2-3 hours, otherwise after 7 days. Drying time depends on weather conditions (humidity and temperature). Allow at least 30 days before cleaning and washing newly painted surfaces with Direct-1.

Tools must be cleaned immediately after use with Spray Gun Solvent T 350.



TECHNICAL CHARACTERISTICS

Viscosity	85 ± 5 KU (ASTM D 562, 25°C)
Density	1,14 ± 0,02 Kg/L (ISO 2811) for white
Gloss	> 90 units @ 60° (ISO 2813)

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr